



## Ultra Carbide, LLC

29550 WM. K. Smith Drive Suite C  
New Hudson, MI 48165

Phone: 248-446-1744

Fax: 248-692-0494

email: sales@ultracarbide.com

website: www.ultracarbide.com

# G-ELIT

Ultra Carbide Inc. /Plant

G-Elit Hartstoffe GmbH

Lübarser Straße 10 -38


13435 Berlin

### Carbide grade: DK 255 F

#### Chemical Composition:

WC 92,00 %

Co 8,00 %



#### Physical Properties:

Density [g/cm<sup>3</sup>]: 14,55 ± 0,20  
(ISO 3369)

Coercive Force [kA/m]: 21,49 ± 2,79  
(ISO 3326) [Oe]:

Magnetic Saturation [0.1µT·m<sup>3</sup>/kg]: 145 ± 10

Hardness [HV 30]: 1720 ± 50  
(ISO 3878) HRA: 92.6 0,2

TRS [N/mm<sup>2</sup>]: 3500 Minimum

K1C [MPa ](m)<sup>1/2</sup>] 9,6 Minimum

Porosity A<02 B<02  
[ISO 4505]

Microstructure Homogenous, no eta-Phase, no free carbon

WC- Grain Size (FSSS) 0,7 µm

Classification K20 US/Buick C1, C9, C5 Coated  
[ISO 513]

Fine grade with high wear resistance suitable for cast iron, hard Al-alloys and Ti-Aluminide.